Amendments to the Claims:

The following listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Original) A coating method of dripping and applying a coating liquid on a coating surface of an object to be coated, while rotating the object to be coated, comprising:

dripping the coating liquid in a ring shape in the vicinity of a circumference on the coating surface of the object to be coated, and thereafter

dripping the coating liquid in a spiral shape toward a geometrical center or an optical center of the object to be coated from the vicinity of the outer circumference.

- 2. (Original) The coating method according to claim 1, wherein the coating surface of the object to be coated has a convex curved shape.
- 3. (Currently Amended) The coating method according to either of claim 1 or 2 claim 1, wherein a viscosity of the coating liquid is 25 to 500 cps at 25°C.
- 4. (Original) A manufacturing method of a photochromic lens of dripping and applying a coating liquid having a photochromic function, on a coating surface of a lens while rotating the lens, and forming a coating film having the photochromic function on the coating surface of the lens, comprising:

dripping the coating liquid in a ring shape in the vicinity of an outer circumference on the coating surface of the lens, and thereafter

dripping the coating liquid in a spiral shape toward a geometrical center or an optical center of the lens from the vicinity of the outer circumference.

- 5. (Original) The manufacturing method of the photochromic lens according to claim 4, wherein the coating surface of the lens has a convex curved shape.
- 6. (Currently Amended) The manufacturing method of the photochromic lens according to either of claim 4 or 5 claim 4, wherein a viscosity of the coating liquid is 25 to 500cps at 25°C.
- 7. (New) The coating method according to claim 2, wherein a viscosity of the coating liquid is 25 to 500 cps at 25°C.
- 8. (New) The manufacturing method of the photochromic lens according to claim 5, wherein a viscosity of the coating liquid is 25 to 500cps at 25°C.